

Werkstoff-Gruppe Material group	WSP -Sorte Insert grade				BCP20M	BCP25M	BCP30M	
	ISO Code							
	Werkstoff Material	Trockenbe- arbeitung Dry machining						
P	Baustahl Structural steel		●	○	190 - 290	175 - 265	160 - 240	
	Vergütungsstahl Heat treated steel		●	○	160 - 230	145 - 215	140 - 190	
	Werkzeugstahl Tool steel		●	○	145 - 210	130 - 190	120 - 175	
	Gehärteter Stahl Hardened steel		●	○	110 - 170		100 - 160	
	Nichtrostender Stahl Stainless steel	austenitisch austenitic	●	○		90 - 150		
M		austenitisch gehärtet austenitic hardened	●	○		60 - 110		
	Grauguss Grey cast iron		●	○		140 - 300		
K	Gusseisen mit Kugelgraphit Nodular graphite cast iron		●	○		100 - 160		
	Aluminium Aluminium		●	○				
N	Kupfer und Kupferlegierungen Copper and copper alloys		●	○				
	Wärmfeste Legierungen Heat resistant alloys		○	●				
S	Titanlegierungen Titanium alloys		○	●				

- empfohlene Anwendung recommended application
○ alternative Anwendung um 30 - 50 % reduzieren
alternative application reduced by 30 - 50 %

	BCP35M P35	BCP40M P40	BCM35M M35	BCM40M M40	BCK15M K15	BCK20M K20	BCN10M N10	BCN15M N15	BWN10M N10
	150 - 230	100 - 220				200 - 300			
	130 - 180	145 - 215				180 - 250			
	110 - 160	130 - 190				160 - 220			
						120 - 180			
	80 - 140	70 - 130	110 - 180	100 - 160					
			80 - 130	70 - 120					
					180 - 360	150 - 320			
					140 - 250	110 - 180			
							500 - 3000	500 - 3000	400 - 2500
							160 - 500	160 - 500	120 - 400
				30 - 70					25 - 80
				30 - 80					30 - 80

WSP Geometrie Insert geometry	Schnitttiefe Cutting depth [mm] a_p max	Vorschub Feed [mm] f_z
MP	1 5 10	0,1 0,2 0,25
MM	1 5 10	0,1 0,18 0,22
MK	1 5 10	0,1 0,2 0,25